

Date of Deposit May 15, 2001.

RECEIVED
09 JUL 2001

JC19 Rec'd PCT/PTO 15 MAY 2001

FORM PTO-1390 (REV. 5-93)		U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE	CASE NO. 11038/3
TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. 371			U.S. APPLICATION NO. (If known, see 37 C.F.R. 1.5) 09/831931
INTERNATIONAL APPLICATION NO. PCT/DK99/00631	INTERNATIONAL FILING DATE 17 November 1999	PRIORITY DATE CLAIMED 17 November 1998	
TITLE OF INVENTION ELECTROCHEMICAL CELL			
APPLICANT(S) FOR DO/EO/US Soren Primdahl, Carsten Bagger, Mette Juhl Jorgensen, Mogens Mogensen, Olga Marina			
Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:			
<p>1. <input checked="" type="checkbox"/> This is a FIRST submission of items concerning a filing under 35 U.S.C. 371</p> <p>2. <input type="checkbox"/> This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371</p> <p>3. <input checked="" type="checkbox"/> This express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).</p> <p>4. <input checked="" type="checkbox"/> A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.</p> <p>5. <input checked="" type="checkbox"/> A copy of the International Application as filed (35 U.S.C. 371(c)(2)).</p> <p>a. <input checked="" type="checkbox"/> is transmitted herewith (required only if not transmitted by the International Bureau).</p> <p>b. <input checked="" type="checkbox"/> has been transmitted by the International Bureau.</p> <p>c. <input type="checkbox"/> is not required, as the application was filed in the United States Receiving Office (RO/US).</p> <p>6. <input type="checkbox"/> A translation of the International Application into English (35 U.S.C. 371(c)(2)).</p> <p>7. <input type="checkbox"/> Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3)).</p> <p>a. <input type="checkbox"/> are transmitted herewith (required only if not transmitted by the International Bureau).</p> <p>b. <input type="checkbox"/> have been transmitted by the International Bureau.</p> <p>c. <input type="checkbox"/> have not been made; however, the time limit for making such amendments has NOT expired.</p> <p>d. <input type="checkbox"/> have not been made and will not be made.</p> <p>8. <input type="checkbox"/> A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).</p> <p>9. <input checked="" type="checkbox"/> An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).</p> <p>10. <input type="checkbox"/> A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)) and/or amendments under Article 34.</p>			
Items 11. to 16. Below concern other document(s) or information included:			
<p>11. <input type="checkbox"/> An Information Disclosure Statement under 37 CFR 1.97 and 1.98.</p> <p>12. <input checked="" type="checkbox"/> An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.</p> <p>13. <input type="checkbox"/> A FIRST preliminary amendment.</p> <p><input type="checkbox"/> A SECOND or SUBSEQUENT preliminary amendment.</p> <p>14. <input type="checkbox"/> A substitute specification.</p> <p>15. <input type="checkbox"/> A change of power of attorney and/or address letter.</p> <p>16. <input checked="" type="checkbox"/> Other items or information: Request, International Application Published Under PCT, Notice Informing the Applicant of the Communication of the International Application to the Designated Offices, Notification Concerning Submission or Transmittal of Priority Document, Information Concerning Elected Offices Notified of Their Election, Notification of Transmittal of the International Preliminary Examination Report, PCT Written Opinion dated August 10, 2000 and Written Opinion dated November 27, 2001</p>			

U.S. APPLICATION NO. 09/831931 (If known, see 37 CFR 1.50)	INTERNATIONAL APPLICATION NO. PCT/DK99/00631	CASE NO. 11038/3
--	---	------------------

17. <input type="checkbox"/> The following fees are submitted: Basic National Fee (37 CFR 1.492(a)(1)-(5)): Search Report has been prepared by the EPO or JPO \$860.00 International preliminary examination fee paid to USPTO (37 CFR 1.492(a)(1)) \$690.00 No international preliminary examination fee paid to USPTO (37 CFR 1.482) but international search fee paid to USPTO (37 CFR 1.492(a)(2)) \$710.00 Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.492(a)(3)) paid to USPTO \$1,000.00 International preliminary examination fee paid to USPTO (37 CFR 1.482) and all claims satisfied provisions of PCT Article 33(1)-(4) \$100.00	<table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <th style="width: 50%;">CALCULATIONS</th> <th style="width: 50%;">PTO USE ONLY</th> </tr> <tr> <td colspan="2" style="height: 150px;"></td> </tr> <tr> <td style="text-align: right;">\$1860</td> <td></td> </tr> </table>	CALCULATIONS	PTO USE ONLY			\$1860	
CALCULATIONS	PTO USE ONLY						
\$1860							

ENTER APPROPRIATE BASIC FEE AMOUNT			
Surcharge of \$130.00 for furnishing the oath or declaration later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(e)).			
Claims	Number Filed	Number Extra	Rate
Total Claims	3- 20 =		x \$ 18.00
Independent Claims	2- 3 =		x \$ 80.00
Multiple dependent claim(s) if Applicable		0	+ \$270.00
TOTAL OF ABOVE CALCULATIONS =			\$1860
Reduction by 1/2 for filing by small entity, if applicable. Verified Small Entity statement must also be filed. (Note 37 CFR 1.9, 1.27, 1.28)			
SUBTOTAL =			\$1860
Surcharge of \$130.00 for furnishing the English translation later than the <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(f)).			\$
TOTAL NATIONAL FEE =			\$1860
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31), \$40.00 per property +			40.00
TOTAL FEES ENCLOSED =			\$1900
			Amount to be refunded
			\$
			charged
			\$1900

a.	<input checked="" type="checkbox"/>	A check in the amount of \$1900 to cover the above fees is enclosed.
b.	<input type="checkbox"/>	Please charge my Deposit Account No. 23-1925 in the amount of \$1900 to cover the above fees. A duplicate copy of this sheet is enclosed.
c.	<input checked="" type="checkbox"/>	The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 23-1925. A duplicate copy of this sheet is enclosed.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.

Send All Correspondence to: Brinks Hofer Gilson & Lione P.O. Box 10395 Chicago, IL 60610	<div style="text-align: center;"> Signature Jasper W. Dockrey Name 33,868 Registration Number </div>
---	--

Title: Electrochemical cell

Technical Field

The invention relates to an electrochemical cell, such as an SOFC cell, comprising a nickel based electrode structure, such as in form of an Ni/YSZ anode, to which Mn
5 has been added.

Background Art

From JP 5-190183 it is known to add Mn to the Ni/YSZ anode in an amount of 5 to 50 metal atom % of the anode material. As a result the reaction resistance R_p of the anode is reduced.

10 Brief Description of the Invention.

The object of the present invention is to show how the reaction resistance R_p can be further reduced as well as how further advantages in form of an increased conductivity and a limited catalytic activity can be obtained.

An electrochemical cell of the above type is according to the invention characterized
15 in that the added amount of Mn to the zone of the electrode extending less than 20 μm from the electrolyte represents 0.5 to 5 metal atom %, preferably 1 to 4 metal atom %, especially 2 to 3 metal atom %.

An electrochemical cell can be produced by applying electrodes onto a carrier electrolyte or electrolyte on a carrier electrode. The cell can be produced by intermediate
20 sinterings or be sintered when more or all the components are assembled.

An electrochemical cell can be used within several fields, said cell comprising an electrolyte, which is also called a membrane, in contact with two electrodes of a

predetermined composition where at least one electrode is subjected to a gas mixture which has a reducing effect compared to air. Below four examples are presented of how the electrochemical, electric and catalytic properties of such a nickel based electrode are of vital importance for the efficiency of the cell.

- 5 i) a solid oxide fuel cell (SOFC) is a catalytic cell mainly comprising an electrolyte with an anode and a cathode on opposed sides. A nickel electrolyte composite is widely used as the anode. The electrolyte is most frequently a Y-doped ZrO_2 (YSZ). The anode is most frequently produced by way of sintering in air, the reason why NiO is used. During
10 operation the NiO is reduced to Ni in the reducing anode gas. The fuel cell can be supplied with a gas, such as hydrogen or methane, and produce current or be driven by means of the current and dissociate for instance water or carbon dioxide.
- 15 ii) An electrochemical reactor can be used for a chemical synthesis by way of a complete or partial oxidation of a compound, such as for instance methane, ethane or methanol. The reactor can be based on electrochemical cells with two electrodes, where at least one electrode, viz. the active electrode, catalyzes the oxidation. This electrode is typically nickel based.
- 20 iii) An oxygen separation membrane can be used for the production of for instance synthesis gas by way of a partial oxidation of for instance methane. This membrane can be a dense electrolyte as stated above or an electrolyte which has been provided with an electronic conductivity, viz. be internally short-circuited, and on which a nickel based electrolyte catalyzes the oxidation. A reactant, such as for instance oxygen, water or
25 carbon dioxide can be mixed into the reducing gas or oxygen can be supplied in ionic form through the membrane. This process can be electrically driven by transmitting a current through the cell, viz. the compact

electrolyte, or the cell can be internally short-circuited, viz. the electrolyte with the electronic conductivity.

iv) As a sensor for measuring the composition of the gas.

5 In the four examples i) to iv) the nickel based electrode has been subjected to a reducing atmosphere, in which a complete or partial oxidation or reduction of a reactant takes place. The fundamental function of the electrochemical cell is thus to oxidize for instance methane, hydrogen or carbon monoxide while delivering an electric current, or to drive the process in the opposite direction by applying a current and
10 dissociating for instance water into hydrogen and oxygen.

The efficiency of the electrode is typically defined by the following three values: A) the power loss associated with the electrode process, B) the electric conductivity of the electrode, and C) the catalytic activity of the electrode.

Below these properties are discussed in connection with nickel based electrodes or
15 catalytically active components used in a fuel cell, an electrochemical reactor and on an oxygen separation membrane or the like.

Definition of problems

A) An improvement of the efficiency of the electrochemical cell and a reduction of the costs give rise to a demand for reducing the power loss
20 ($W_{\text{TAB}} = R_p i^2$) associated with the electrode process and below expressed by the reaction resistance R_p also called the polarization resistance. It turned out that an Ni/YSZ composite electrode with respect to function, but not necessarily to production can be divided into two zones with different primary functions. The electrode is electrochemically active in
25 a range of 10 to 20 μm from the compactly sintered electrolyte, which

means that here the reactants are reacted by way of oxidation reduction while releasing or receiving electrons. This layer is associated with the lowest achievable reaction resistance R_p for the electrode in question.

5 B) The primary function of the superposed electrode structure is contacting and as electron conductor because the reactants in the active layer are only reacted in so far as electrons can be transmitted to or from the electrode. This conductivity is substantial because a predetermined distance of the magnitude of mm or more can exist in the technical structure of the electrochemical cell between the contact points of the electrode and the structure establishing the electric contact to the cell.

10 C) As far as an SOFC driven on natural gas or methane is concerned, the endothermal steam reforming reaction should for optimizing reasons be carried out on or adjacent the active cell where heat is generated. The strong catalytic properties of nickel have the effect that the steam reforming reaction on a nickel based electrochemical cell typically occurs over the first few mm of the electrode adjacent the gas inlet, whereby this part of the system is strongly cooled. As a result, thermal gradients arise in the system which in turn involves a risk of breakings. Accordingly there is a demand for a possibility of suppressing the activity of a specific amount of nickel in the electrode with respect to the catalytic reaction of hydrocarbons. This demand applies to the entire electrode structure and primarily to the superposed electrode part which handles the conductivity of the electrode as this part presents the largest nickel surface.

Background Art

25 A) The composite Ni/YSZ electrode for SOFC has been the object of several optimizing studies with respect to microstructure, particle size relation-

ship, sintering temperature and quantitative ratio of the two materials. Ni/YSZ composite anodes are known with a reaction resistance R_p lower than 0.10 to 0.15 Ωcm^2 at 1000°C in hydrogen with approximately 3% water.

- 5 An R_p lower than above has been obtained by using ruthenium in stead of nickel, but ruthenium is relatively cost-intensive and difficult to process for the purpose.

In stead of the typical ZrO_2 based electrolyte, it is possible to use a mixed conductor based on for instance PrO_x , CeO_2), whereby the R_p is reduced. Again, the raw materials are relatively expensive.

- 10 B) The demand for a high conductivity in the electrode can be met by using an Ni/YSZ composite with a high content of Ni or by sintering the electrode structure at a high temperature in such a manner that the nickel particles are brought into a good contact. However, it is not advantageous to have a too high content of nickel because the thermal coefficient of expansion (TEC) of the electrode is thereby increased. As a result it moves away from the electrolyte both in the oxidized state and in the reduced state. Furthermore, it has been demonstrated that fractures caused by the difference in TEC easily propagate between the electrode and the compactly sintered electrolyte when the sintering temperature is higher than stated above. Finally, the content of Ni should be low in order to minimize the tension in the structure in case the nickel content of the electrode unintendedly oxidizes during operation.

- 20 C) No technically suitable method is known for lowering the catalytic properties of nickel apart from a lowering of the nickel content/the nickel surface, which in general has a negative effect on the polarisation resistance R_p of the electrode and the electric conductivity.

Brief Description of the Invention

The above three problems A) to C) can to a considerable degree be solved by adding MnO_x to the nickel based electrode or the nickel based catalytic component. Here and below the expression MnO_x is used for all possible components which can supply the element Mn bearing in mind that under usual operational conditions for such structures nothing but Mn-oxides or a mixed metallic oxide containing Mn exist.

The problems B) and C) are solved by means of the features indicated in claim 2.

Brief Description of the Drawings

The invention is explained in greater detail below with reference to the accompanying drawings, in which

Fig. 1 is a diagrammatic cross sectional view of a symmetrical electrochemical cell comprising an electrolyte and two identical electrodes, each electrode including three electrode layers,

Fig. 2 illustrates the electric connections to the symmetrical cell used for characterizing the polarisation resistance R_p of the electrodes,

Fig. 3 shows test data in form of an impedance spectrum corrected for the area of the electrode. The polarisation resistance R_p of the electrode presents approximately $2/3$ of the distance between the axis points of intersections on the abscissa,

Fig. 4 shows an equivalent circuit used for curve adjustment of the test data in Fig. 3, where L is an inductance, R_s a serial resistance in the electrolyte, R_1 and R_2 together present the polarization resistance R_p , whereas R_D is the diffusion resistance in the gas above the electrodes. Q is a constant phase element representing a non--

ideal capacitance associated with the indicated resistances,

Fig. 5 is a sectional view through a semi-cell for characterising the inplane conductivity of the electrode, where an upper electrode layer of a predetermined thickness has been superposed an electrolyte with an active electrode layer. The
5 thickness of the active electrode layer is preferably less than $20\mu\text{m}$,

Fig. 6 illustrates a contacting so as to characterize the inplane conductivity of an upper electrode layer on the semi-cell of Fig. 5. Platinum wires with insulating aluminium pipes wound thereon are pressed against the electrode surface of a weight load. The platinum wires represent four contacts of a square arrangement, the
10 conductivity of thin layers being measurable between said contacts,

Fig. 7 illustrates an arrangement for measuring the catalytic activity of a powdered electrode layer. A gas mixture is established with mass flow valves and is carried successively through the following elements through pipes: A bobble bottle with water on a thermostatically controlled oil bath, whereby the water content in the gas
15 is increased, a powdered catalyst on a bed of inert material in a heated U-shaped quartz pipe, in which a catalytic reaction occurs, a cold trap, in which the water content in the gas is reduced, and a gas chromatograph, in which the composition of the gas is analysed,

Fig. 8 shows measuring data, viz. the catalytic activity expressed as the reforming
20 speed versus the content of MnO_x expressed as metal atom% of Mn in the electrode layer,

Fig. 9 is a cross sectional view of an electrochemical cell, where an electrolyte has been coated with two cathode layers on one side and two anode layers on the opposite side,

Fig. 10 is a sectional view of an experimental contacting of the cell of Fig. 9. The electrode surfaces of the cell are coated with a non-sintered contact layer on both anode and cathode, said layers ensuring the contact to a woven platinum grid which is applied onto both electrode surfaces,

- 5 Fig. 11 is a sectional view of an arrangement in an oven for an electric characterizing of an electrochemical cell. The contacted electrochemical cell of Fig. 10 has been mounted between gas distribution plates with ribs and openings, said gas distribution plates in turn being mounted between two sets of concentric aluminium pipes. Gases are fed to the electrodes through the outer pipes and removed through the inner
10 pipes,

Fig. 12 shows measuring data, viz. area corrected voltage curves for the edge voltage V_K and the central voltage V_C , respectively. The DC resistance of the cell is calculated as the negative average inclination over the entire measured interval.

Best Mode for Carrying Out the Invention.

- 15 The addition of MnO_x to the active electrode layer, which preferably represents less than $20\mu m$, and the superposed layers 19, 20, which can be of a predetermined thickness, has been documented by way of a number of examples.

- The polarization resistance R_p measured at $850^\circ C$ and $1000^\circ C$ in hydrogen with 3% water for an Ni/YSZ cermet anode has been reduced by addition of MnO_x by
20 way of 1) impregnation of a sintered electrode, 2) application onto the electrolyte surface prior to the application and sintering of the electrode, and 3) admixing into the anode slurry prior to application and sintering. At $850^\circ C$ R_p has been reduced from $105\text{ m}\Omega\text{cm}^2$ to $59\text{ m}\Omega\text{cm}^2$, and at $1000^\circ C$ R_p has been reduced from $79\text{ }\Omega\text{cm}^2$ to $20\text{ }\Omega\text{cm}^2$.

- The electronic conductivity of an Ni/YSZ electrode layer has been increased by addition of MnO_x from 14 to 390 S/cm at 20°C and from 2.5 to 60 S/cm at 1000°C.
 - The catalytic activity of an Ni/YSZ cermet electrode layer for steam reformation of methane has been reduced by addition of MnO_x from 0.3 to 0.005 $\mu\text{molmin}^{-1}\text{g}^{-1}$.
 - The polarization resistance R_p of an Ni/YSZ anode on an electrochemical cell has been reduced by addition of MnO_x to the anode from 0.25 Ωcm^2 to maximum 0.08 Ωcm^2 at 850°C.
- 10 Below the examples are discussed in detail:

Reduction of R_p for Ni based electrode

The electrodes are applied onto the electrolyte by way of airborne injection of a particle suspension, but other techniques, such as serigraphy and painting are also suitable. The suspension is provided in the solvent ethanole by means of the dispersant polyvinyl butyral, but other solvents and dispersants are also suitable. An electrode comprises one or more layers, and particle suspensions of different compositions can be used for these layers. A suitable particle size distribution and homogeneity are obtained by ball grinding the suspension. After spraying of one or more particle suspensions, the electrode is subjected to a sintering. The electrode can furthermore be admixed additives by way of application of intermediate layers or postimpregnation by means of dissolved salts or suspensions.

In order to illustrate the effect of adding MnO_x to Ni-based electrodes, a reference electrode without MnO_x and test electrodes with MnO_x have been produced, cf. Table

- 1A. The electrodes comprising a first, a second and a third electrode layer 18, 19, 20 are applied onto both sides of sintered 8YSZ (ZrO_2 doped with 8 mol% Y_2O_3) electrolytes 1, cf. Fig. 1. The electrolytes 1 are of a thickness of 160 to 180 μm . A contact face 22 is provided between the electrolyte 1 and the first electrode layer 18.
- 5 The produced cells are fragmented into almost square elements of an area of approximately 0.1 to 0.2 cm^2 and mounted between four platinum wires 6 in such a manner that two elements are provided on the central portion of each electrode surface, cf. Fig. 2. The cells are placed in an oven in a controlled atmosphere of hydrogen moistened with 3% water at 25°C. The impedance of the cells is measured
- 10 by impedance spectroscopy at open voltage ($\eta=0$) at 850°C and 1000°C. Such a measuring is illustrated in Fig. 3.

A curve adjustment of the impedance measurements were performed by means of the program "Equivalent Circuit", an equivalent circuit being adjusted to the test data. The equivalent circuit includes capacitances C, inductances L, resistances R and

15 constant phase elements Q.

The equivalent circuit used for the curve adjustment is shown in Fig. 4, where L is an induction also covering phase errors in the measuring equipment at high frequencies, R_s is a serial resistance including a resistance substantially in the electrolyte, R_1 & Q_1 and R_2 & Q_2 represent limiting steps in the electrode reaction,

20 whereas R_D & Q_D represents the gas phase diffusion resistance outside the anode structure. The reaction resistance R_p is then calculated for the electrode as

$$R_p = (R_1 + R_2) \cdot A \cdot 1/2$$

where A is the area of the cell, and the factor $1/2$ is caused by both electrodes on the cell being part of the measuring.

Table 1A

Type of element	The composition of the first layer, metal atom%	Sintering and thickness	The composition of the following layer, metal atom%	Sintering and thickness	R _p , 850°C, mΩcm ²	R _p , 1000°C, mΩcm ²
Reference element	67.5% NiO, 32.5% 8YSZ	1300°C/2h 15μm	67.5% NiO, 32.5% 8YSZ	2 x 1300°C/2h 35μm	105	79
Impregnation after sintering	65.8% NiO, 31.8% 8YSZ, 2.4% MnO ₂ □	1300°C/2h 15μm	65.8% NiO, 31.8% 8YSZ, 2.4% MnO ₂ □	2 x 1300°C/2h 35μm	86	20
Additive on the electrolyte surface	64.4% NiO, 31.0% 8YSZ, 4.6% MnO ₂ &	1300°C/2h 10μm	67.5% NiO, 32.5% 8YSZ	2 x 1300°C/2h 37μm	74	43
Additive in anode layer	67.5% NiO, 32.5% 8YSZ 2.1% MnO ₂ #	1300°C/2h 5 to 6 μm	67.5% NiO, 32.5% 8YSZ	2 x 1300°C/2h 50μm	59	66

□ Mn added as solution of Mn(Ac)₂ · 4H₂O by impregnation of the sintered electrode structure.

& Mn added as solution of Mn(Ac)₂ · 4H₂O painted on electrolyte prior to spraying of first anode layer.

15 # Mn added as solution of Mn(NO₃)₂ · 4H₂O in the particle solution forming the first electrode layer.

Improved conductivity of Ni/doped ZrO₂ based electrode

The conductivity in the plane of the electrode can be a limiting factor for the conductivity of said electrode when the distance between contact points to the surrounding contacting structure exceeds the thickness of the electrode structure. The latter is often the case where gas access to the electrode is required. It is typically necessary to apply a nickel based layer onto an electrochemical cell with a nickel based active electrode of a poor thickness, i.e. below 20 μm , in order to ensure a sufficient in-plane conductivity.

Such a composite electrode layer can be applied by way of spraying of a particle suspension as stated above. Other techniques are also suitable. After the application of one or more particle suspensions, the structure can be subjected to a sintering, if necessary.

In order to document the positive effect of MnO_x on the inplane conductivity of a composite nickel based electrode layer, two Ni/8YSZ (ZrO_2 doped with 8 mol% Y_2O_3) electrode layers are produced with and without MnO_x . The comparison appears from Table 1B. The electrode layers are sprayed onto 10 to 20 μm thin Ni/8YSZ anodes on 8YSZ electrolytes, cf. Fig. 5 showing the electrolyte 1, onto which an active electrode layer 23 and an electrode layer 24 have been applied.

The produced semi-cells are fragmented into elements of an area of approximately 1 to 2 cm^2 , and four Pt point connections are established by means of weight-loaded Pt wires 6 wound about aluminium pipes 7, cf. Fig. 6 showing the weight load 26. The element is placed in an oven in an atmosphere of 9% hydrogen in nitrogen with 3% water, and heated to 1000°C. The conductivity of the electrode layer 8 σ (at 1000°C) is determined by way of a square four-point measuring (Van der Pauw) technique, which is calibrated on a metal element having a well-known conductivity.

After the above characterization the elements are cooled under reducing conditions,

Table 1B

Type of element	Composition of the electrode layer, metal atom%	8YSZ Particle size	Sintering	$\sigma(20^{\circ}\text{C})$, S/cm	$\sigma(1000^{\circ}\text{C})$, S/cm
Reference element	67.5% NiO, 32.5% 8YSZ	20% 0.3 to 0.4 μm 80% 10 to 50 μm	1250°C/2h	470	50
Test element	64.4% NiO, 31.9% 8YSZ, 4.1% MnO₂#	20% 0.3 to 0.4 μm 80% 10 to 50 μm	1250°C/2h	1060	150
Reference element	67.5% NiO, 32.5% 8YSZ	40% 0.3 to 0.4 μm 60% 10 to 50 μm	1250°C/2h	14	2.5
Test element	64.4% NiO, 31.9% 8YSZ, 4.1% MnO₂#	40% 0.3 to 0.4 μm 60% 10 to 50 μm	1250°C/2h	390	60

Added as $\text{Mn}(\text{NO}_3)_2 \cdot 4\text{H}_2\text{O}$

Catalytic activity of Ni-based electrode

For nickel based electrodes and catalytic elements, where an electronic conductivity is to be maintained while the catalytic activity of nickel is to be limited, it is not possible to reduce the amount of nickel much below 30% in a porous structure.

- 5 Instead the catalytic activity of present nickel can be reduced. Below it has been documented that this reduction of catalytic activity for nickel can be provided by adding MnO_x . A fine-grained Ni/8YSZ (ZrO_2 doped with 8 mol% Y_2O_3) based structure is produced by mixing NiO, 8YSZ and a water-based binder with water to a viscous mass and by rolling this mass into a plate of a thickness of 1 mm and
- 10 sintering said plate at $1350^\circ\text{C}/8$ hours. A number of such plates has been produced by admixing various amounts of $\text{Mn}(\text{NO}_3)_2 \cdot 4\text{H}_2\text{O}$. The tested compositions appear from Table 1C. The sintered plates are crushed in a mortar, and by way of screening a fraction of 0.4 to 1.0 mm has been removed and tested as catalyst for steam re-forming of methane.
- 15 The catalyst is admixed quartz sand in the ratio 1:5. This mixture is placed on a bed of pure quartz sand in a U-shaped quartz pipe ($\varnothing_i=5\text{mm}$), through which a gas mixture is fed to a gas chromatograph, cf. Fig. 7. The gas mixture is established by a mixing of pure gases through thermal mass flow meters. Subsequently the gas is moistened with water in a bobble bottle 9 on a thermostatically controlled oil bath 10.
- 20 Thereafter the gas is kept at an increased temperature until it has passed the catalyst 11 followed by a quartz ring 27 so as to prevent condensation. The quartz pipe 12 is placed in an oven 13, and the sample is heated to 900°C in a flow of 9% hydrogen in nitrogen. The sample is stabilised for 24 hours in pure hydrogen with approximately 3% water (saturation at 25°C) and then cooled to 850°C . The gas in the pipe
- 25 is replaced by 67% methane + 33% water (saturation at 88°C). When the gas has passed the catalyst 11, the majority of the water is condensed out into a cold trap 15 (8°C), and the composition of the remaining amount of gas is tested in a gas

chromatograph 16. The gas chromatograph 16 (HP 5890 Series II) is equipped with a 6 foot Porapak Q column, a detector measuring thermal capacity (TCD), as well as an HP3396A integrator. The reformed portion of the methane gas R_{CH_4} is calculated on the basis of a carbon balance in the gas leaving the catalyst 11,

$$5 \quad R_{CH_4} = (C_{CO_2} + C_{CO}) / (C_{CO_2} + C_{CO} + C_{CH_4})$$

where C_x indicates the concentration of methane (C_{CH_4}), carbon dioxide (C_{CO_2}) and carbon monoxide (C_{CO}), respectively. R_{CH_4} is standardized relative to the weighed amount of Ni/8YSZ catalyst and the composition and speed of the input gas in the pipe surrounding the catalyst 11, whereafter the reforming speed in $\mu\text{molmin}^{-1}\text{g}^{-1}$ are found. The calculated values based on the measurements are indicated in Fig. 8.

Table 1 C

Type of element	Composition of the catalyst, metal atom%	Sintering
Reference element	67.4% NiO, 32.6% 8YSZ	1350°C/8h
Test element	65.0% NiO, 31.4% 8YSZ, 3.6% MnO_2 #	1350°C/8h
Test element	63.5% NiO, 30.6% 8YSZ, 5.9% MnO_2 #	1350°C/8h

Added as $\text{Mn}(\text{NO}_3)_2 \cdot 4\text{H}_2\text{O}$

Demonstration of electrochemical cell

20 For the power production of a fuel gas and air, an electrochemical cell, cf. Fig. 9, with MnO_x is produced in the following manner:

- A compact 8YSZ (ZrO_2 doped with 8 mol% Y_2O_3) electrolyte of a thickness of $170\mu\text{m}$ is produced by sintering at 1350°C after film casting.

- A particle suspension containing 55.8 w/o of 8YSZ and 44.2 w/o of NiO is sprayed onto one electrolyte side, viz. the anode side, and sintered at 1300°C/2h, which results in a porous layer of a thickness of approximately 15 μm .
- 5 - A second particle suspension containing 42.6 w/o of 8YSZ and 53.6 w/o of NiO and 3.8 w/o of MnO_2 (3.9 metal atom%) added in form of $\text{Mn}(\text{NO}_3)_2 \cdot 4\text{H}_2\text{O}$ is sprayed twice onto the initially applied layer on the anode side and sintered after each spraying at 1200°C/2h, whereafter it forms a porous layer of a thickness of approximately 35 μm .
- 10 - A third particle suspension containing 40 w/o of 3YSZ and 60 w/o of $(\text{La}_{0.85}\text{Sr}_{0.15})_{0.90}\text{MnO}_3$ is sprayed onto the opposite side of the electrolyte, viz. the cathode side, and sintered at 1100°C/2h, whereafter it forms a porous layer of a thickness of approximately 10 μm .
- A fourth particle suspension containing $(\text{La}_{0.85}\text{Sr}_{0.15})_{0.90}\text{Mn}_{1.10}\text{O}_3$ is sprayed onto
15 the active cathode in two layers, each layer being sintered at 1100°C/2h, whereafter it forms a porous layer of a thickness of approximately 30 μm .

The efficiency of the cell is characterized as follows, cf. Fig. 10.

- The anode side is provided with a contact layer in form of an NiO suspension which is sprayed thereon in a layer of a thickness of approximately 50 μm and
20 which is not sintered.
- The cathode side is provided with a contact layer in form of a 75 μm thick film cast layer, which is applied by way of softening in ethanole, and which is not sintered.
- Circular, woven Pt grids 29 of an area of 10.0 cm^2 are symmetrically mounted on

both electrode surfaces.

As a result the cell is efficiently contacted across the entire electrode surface through the platinum grids 29.

The cell with the contacting is mounted between two plane gas distribution plates 30 with openings and ribs which ensure gas access to the electrodes. The cell and the contacting and the gas distribution plates 30 are mounted between two sets of aluminium pipes 31 in an oven, cf. Fig. 11. The cell is heated to a temperature of 1050°C. The temperature is measured by means of thermal elements arranged 1 mm above the centre of the cell.

10 The cathode side is fed with air, whereas the anode side is fed with hydrogen moistened with 1.2% water at 11°C. The gases are fed through the outer pipes and removed through the inner pipes. The voltage across the cell can be measured at the edge V_K and the centre V_C of the electrodes through wires without current. Current is collected from the cell through the platinum grids 29 and separate conduits by
15 loading with external resistances, and a current-voltage curve, cf. Fig. 12, can be taken. The negative inclination of the current-voltage curve presents the DC resistance of the cell, here approximately $0.63 \Omega\text{cm}^2$ estimated conservatively across the entire measured interval.

The DC resistance of the cell includes a) electrolyte resistance (estimated to be $0.35 \Omega\text{cm}^2$ for $170 \mu\text{m}$ 8YSZ at 850°C, b) the reaction resistance of the cathode (estimated to $0.20 \Omega\text{cm}^2$ as the optimal measuring for this type of cathode), c) the reaction resistance of the anode, and d) the resistance in the contacting of the cell. The measuring d) cannot be measured separated, and it is here assumed to be $0.00 \Omega\text{cm}^2$. Subsequently, maximum $0.08 \Omega\text{cm}^2$ of the DC resistance of the cell remains, which
25 can be ascribed to the Ni-based anode, which has been admixed MnO_x .

Reference cells are produced in the same manner apart from 1), MnO_x has not been

added, and 2) the two outermost anode layers have been sintered at 1300°C/2h in order to ensure the conductivity in stead of only 1200°C/2h, and 3) the cathode has been sintered at 1300°C. These reference cells provide in connection with an identical test at best a DC resistance of 1.00 $\Omega \text{ cm}^2$. It is possible to derive a reaction

5 resistance of the anode of 0.25 $\Omega \text{ cm}^2$ from the latter in the same manner when it comes to Ni-based anodes without the addition of MnO_x .

T 05 T 50 T 66 T 66 0

Claims

1. An electrochemical cell, such as an SOFC cell, including a nickel based electrode structure, such as for instance in form of an Ni/YSZ electrode, to which Mn has been added, c h a r a c t e r i z e d in that the added amount of Mn to the active zone of the electrode extending less than 20 μm from the electrolyte represents 0.5 to 5 metal atom%, preferably 1 to 4 metal atom%, in particular 2 to 3 metal atom%.
2. An electrochemical cell as claimed in claim 1, c h a r a c t e r i z e d in that the added amount of Mn in the part of the electrode spaced more than 20 μm from the electrolyte represents 0.5 to 10 metal atom%, preferably 1 to 6 metal atom%, in particular 4 to 5 metal atom%.




Fig. 1






Fig. 2

Fig. 3



*Fig. 4*




Fig. 5




Fig. 6




Fig. 7




Fig. 8




Fig. 9




Fig. 10

FIG. 11




Fig. 11




Fig. 12



**SUPPLEMENTAL
DECLARATION FOR PATENT APPLICATION**

Case No. 11038/3

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

Electrochemical cell, the specification of which:

- ☐ is attached hereto.
- ☒ was filed on 17 November 1999 as Application Serial No. PCT/DK99/00631
- ☐ and was amended on _____ (if applicable).

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to the patentability as defined in Title 37, Code of Federal Regulations, § 1.56(a).

I hereby claim foreign priority benefits under 35 U.S.C. § 119(a)-(d) or § 365(b) of any foreign application(s) for patent or inventor's certificate or § 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application on which priority is claimed:

Prior Foreign Application(s)

Priority Claimed

PA 1998 01497

Denmark

17 November 1998

☒

☐

(Number)

(Country)

(Day/Month/Year Filed)

Yes

No

I hereby claim the benefit under 35 U.S.C. § 119(e) of any United States provisional application(s) listed below:

(Application Serial No.)

(Filing Date)

I hereby claim the benefit under 35 U.S.C. § 120 of any United States application(s), or § 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of 35 U.S.C. § 112, I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR § 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of this application:

(Application Serial No.)

(Filing Date)

(Status-patented, pending, abandoned)

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Inventor's Signature

Full name of sole or first inventor

Residence

Citizenship

Post Office Address

Søren Sørensen

Date: 30 April 2001

PRIMDAHL, Søren

Skovkrogen 2, DK-3400 Allerød, DENMARK

DENMARK

Skovkrogen 2, DK-3400 Allerød, DENMARK

BRINKS HOFER GILSON & LIONE

P.O. Box 10395

Chicago, IL 60610

(312) 321-4200

Jørgen Siiger, legal representative

Case No. 11038/3

Date: 30 April 2001

Inventor's Signature

Full name of second joint inventor, if any

Residence

Citizenship

Post Office Address

Jørgen Siiger
BACCHER, Carsten

Hvedevænget 79, DK-2980 Kokkedal, DENMARK

DENMARK

Hvedevænget 79, DK-2980 Kokkedal, DENMARK

Inventor's Signature

Full name of third joint inventor

Residence

Citizenship

Post Office Address

Mette Juhl
JØRGENSEN, Mette Juhl

Date: 30 April 2001

Guldborgvej 13, DK-4000 Roskilde, DENMARK

DENMARK

Guldborgvej 13, DK-4000 Roskilde, DENMARK

Inventor's Signature

Full name of fourth joint inventor

Residence

Citizenship

Post Office Address

Mogens Mogens
MØGENSEN, Mogens

Date: 30 April 2001

Krogenlundvej 10, DK-3540 Lyngø, DENMARK

DENMARK

Krogenlundvej 10, DK-3540 Lyngø, DENMARK

Inventor's Signature

Full name of fifth joint inventor

Residence

Citizenship

Post Office Address

O. Marina
MARTINA, Olga

Date: 30 April 2001

Bogholder Alle 82, 2.th., DK-2720 Vanløse, DENMARK

DENMARK

Bogholder Alle 82, 2.th., DK-2720 Vanløse, DENMARK

Inventor's Signature

Full name of sixth joint inventor

Residence

Citizenship

Post Office Address

Date:

Inventor's Signature

Full name of seventh joint inventor

Residence

Citizenship

Post Office Address

Date:

rev. Dec.-99

C:\TEMP\0002057.frm

Case No. 11038/3

Inventor's Signature

Jørgen Siiger

Date:

19 Nov 2001

Full name

SIIGER, Jørgen; legal representative of the deceased inventor

Citizenship

DENMARK

Residence


Hvedevænget 79, DK-2980 Kokkedal, DENMARK

Post Office Address

Hvedevænget 79, DK-2980 Kokkedal, DENMARK

PN: 2

United States Patent & Trademark Office
Office of Initial Patent Examination -- Scanning Division



Application deficiencies found during scanning:

☐ Page(s) _____ of _____ were not present
for scanning. (Document title)

☐ Page(s) _____ of _____ were not present
for scanning. (Document title)

☐ *Scanned copy is best available.*

Illustration is too dark